


# Series **Borneo**




# Borneo Pearl Mate 60x120 SI Rc

60x120 SL RC



## Technical Data



Series: BORNEO  
Product: Borneo Pearl Mate 60x120 SI Rc  
Size: 60x120 SL RC  
Sales group G.1093  
Type: Porcelain tiles

Type of material Neutral Body  
Slipperness R: R9A  
Class: Class 1  
UPEC:  
Finish: MATT

Size	Product type	Pcs/Box	M2/Box	Kg/Box	Boxes/Pallet	M2/Pallet	Kg/Pallet
60x120 SL RC	Field Tile	2	1,440	29,389	36,000	51,840	1058,004

Please note: the contents of this packaging list are for guidance only, the contents of the packaging may vary. Please consult our sales staff for the exact list.

**Technical Data**

**Borneo Pearl Mate 60x120 SI Rc**

Family: **Porcelain tiles MATT**  
Absortion Group: **Bla**  
Size: **60x120 SL RC**  
Worz Size (mm): **1200 x 600 x 9**



**PHYSICAL CHARACTERISTICS**

CHARACTERISTICS	STANDARD	VALUE
Dimensional tolerances and surface appearance	UNE-EN-ISO 10545-2	Complies with the standar
Water Absortion	UNE-EN-ISO 10545-3	E<0,5%
Breaking strenght (N)	UNE-EN-ISO 10545-4	>1300
Flexural tensile strengthn (N/mm2)	UNE-EN-ISO 10545-4	>=35
Resistance to abrasion (PEI)	UNE-EN-ISO 10545-7	4
Thermal shock resistance	UNE-EN-ISO 10545-9	Complies with the standar
Cracking resistance	UNE-EN-ISO 10545-11	Complies with the standar
Frost resistance	UNE-EN-ISO 10545-12	Complies with the standar
Scratch hardness according to Mohs	UNE-EN-ISO 67101	5
Slipperness resistance   Pendulum	UNE-EN 16165:2022 anexo C	Clase 1
Slipperness resistance   Inclined platform	UNE-EN 16165:2022 anexo B	R9
Slipperness resistance   Barefoot areas	UNE-EN 16165:2022 anexo A	A
Reaction to fire	UNE-EN-ISO 13501-1	A1 - A1 FL
DCOF	DCOF	<0,42

**CHEMICAL CHARACTERISTICS**

CHARACTERISTICS	STANDARD	VALUE
Resistance to staining	UNE-EN-ISO 10545-14	Complies with the standars
Resistrance to chemicals and pool treatment products	UNE-EN-ISO 10545-13	Complies with the standars
Resistance to High concentration acids and bases	UNE-EN-ISO 10545-13	MIN HB
Resistance to Low concentration acids and bases	UNE-EN-ISO 10545-13	MIN LB